



1. GENERAL:

Endura EX-2C FC Topcoat Gameline coating is a flexible two-component type polyurethane paint. Its properties of high gloss, flexibility, color(s) and excellent gloss retention make this coating ideally suitable for **G-Court** sport floor surfaces.

Coverage on the **G-Court** sport floor surface is approximately 400 linear feet of 2" wide gamelines per unit of paint. (A unit consists of 1 quart of EX-2C FC Topcoat Component A mixed with ½ quart of Special Component B)

2. SURFACE PREPARATION:

- a. Ensure that the floor is thoroughly scrubbed and free of any wax, oil, or lint. Mark off the gymnasium floor in accordance with game requirements as shown on architectural drawings. Game lines shall be accurate to layout and width of lines as indicated on plans. Apply solvent resistant masking tape (3M 233 + is recommended tape), and roll the tape very firmly to ensure the best adhesion.
- b. Endura Prepare Thinner II is an adhesion promoter designed to ensure adhesion on vinyl or linoleum surfaces.**
- c. Apply Endura Prepare Thinner II to the cleaned gameline surface with a clean lint free rag or paint brush. The application must be **THOROUGH** and **WET** the entire gameline surface. Care should be taken to ensure the Prepare Thinner II not be applied to areas not to be painted. The first coat of Endura gameline coating should NOT be applied for at least 1 hour.

Note: If the prepared surface is allowed to dry longer than 24 hours an additional application of the Prepare Thinner II must be re-applied as noted. Failure to do so will result in compromised adhesion and adhesion failure of the game lines.

3. PAINT APPLICATION:

a. Application Temperatures

Use the onsite HVAC unit to maintain ambient temperature and flooring surface temperature at normal application conditions of 18°C (65°F) to 24°C (75°F) at 50% Relative Humidity. For higher humidity above 85% use EX-2C Slow Thinner (5-15%) and/or Endura Retarder. It is important that the temperature of the mixed paint be between 20-24 °C (72° F - 75° F) as it greatly affects viscosity.

Temperatures above or below recommended conditions will decrease or increase the length of drying time.

Surface must be completely dry -Do not apply over moist or damp surfaces.

Do not mix more than is required for a 3-6 hour period. We suggest that the two-part paint be mixed with a power drill. Let it stand for half an hour before application.

b. Application Equipment

Pure bristle brush or foam brush is recommended. On large jobs a short nap 1/8" roller may be used taking caution to ensure no air entrapment between paint and the floor.

c. Application Procedure

Due to the texturing on the surface of the floor some bleeding of the paint may occur even if the tape is thoroughly pressed down.

The **application of** a single coat of CLEAR 100 SFC to the line area that is to be painted **will help eliminate this problem.** This creates a "barrier" that will prevent the colored paint from running under the tape. Please note; the CLEAR 100 SFC must be applied over the inside edge of the tape to **stop the bleeding of the paint.** Allow the Clear 100 SFC to dry 2 hours (but not more than 24 hours) before applying the first color coat. If the Clear 100 SFC is allowed to dry longer than 24 hours it will need to be scuffed before application of the first coat of colored paint.

This is not a required step but will **help** ensure crisp gameline color edges. A unit of CLEAR 100 SFC represents 1 quart of EX-2C Component A combined with 1/2 quart of Special Component B.

Check to see if color is correct before combining EX-2C Component A and Special Component B. Apply by brush if possible rollers **may cause air entrapment. A Unit represents 1 quart of EX-2C Component A combined with 1/2 quart of Special Component B.**

Apply two thin wet coats with each coat at a wet film thickness of 50-60 microns (2- 2 ½ mils). Drying time in between coats should be a minimum of 30 minutes.

Masking tape should be removed as soon as the paint has dried sufficiently to be "tacky". The tape will be difficult to remove if the paint is allowed to cure and ragged line edges will occur.

If Endura EX-2C FC Topcoat is allowed to dry longer than 24 hours at normal temperatures, abrade with sandpaper or scotch bright scuff pad before additional applications of topcoat.

4. CURING RATE

(Normal temperature 20 °C (70°F) to 50% R.H.)

No traffic should be permitted on the newly applied coating for at least 72 hours. Only light traffic without footwear should be permitted for the first 7 days.

After 7 days and up to 30 days the floor may only be dust mopped or lightly damp mopped to remove dust, light debris, etc.

5. SCRUBBING

Do not scrub the floor for at least 30 days after the application of the Endura EX-2C FC Topcoat Game lines

Note: The cleaning solution should be a non-abrasive, phosphate free, biodegradable type and diluted to the manufacturers' recommended directions.

Note: Take time and be prepared before starting the job. A proper work schedule that meets all the job requirements is very important.

Correcting problems with gameline application after the installation can be very difficult, expensive and time consuming.

For technical assistance, please contact CanAm Coatings Ltd. at 619-876-3657.

PHYSICAL PROPERTIES

Resistance to:

- Solvents: Excellent
- Organic chemicals: Very good
- Acids and alkalis: Excellent
- Temperature variations: Excellent

Temperatures:

- 40°C to 200°C maximum
- 40°F to 390°F maximum

Flash point:

- 4°C (25°F)

Colors:

- Available in 9 high gloss solid colors. Special matched colors also available in when requested.

Viscosity of the mix:

- 20-30 sec. #4 Ford Cup.

Pot life:

- 3 to 6 hours.

Note: Once mixed, adding solvent cannot extend pot life.

Clean Up:

- EX-2C Thinner.

Shelf Life:

- Endura EX-2C FC Topcoat Component A will keep indefinitely. Special Component B will keep at least 12 months in original unopened containers depending on storage conditions. Store in cool dry place.

Centaur Floor Systems

135 Chapala Street,
Santa Barbara, CA 93101
Toll-Free: 800-536-9007
Ph: 805-957-0182
Fax: 805-957-0125
www.centaurfloors.com