

PuzzleTile Specs

A. Weight: Approx. 2 lbs/sq. ft. at 8mm thickness

Density: 60 lbs/cu. ft. tiles

Shore A Hardness ASTM Test: 55

Compression at 100 psi: 5 to 15

Recovery: 85 min.

Electric Conductivity: 1.1 x 10.2

Chemical Resistance: Unaffected by most acids and chlorine.

Abrasion Resistance: (2100 cycl): .5150

Coeffi cient of Friction: .057 dry; .072 wet

Compression Endurance: 10,000 cycles with 4 - 9 ton load

Acoustic Rating: Superior

Colors: Gray, Blue and Black

New York State Fire Gas Toxicity Test: #09300-900216-4006

Centaur

Floor Systems

135 Chapala Street,

Santa Barbara, CA 93101

Toll-Free 1-800-536-9007

Ph: 805-957-0182

Fax: 805-957-0125

info@centaurfloors.com

www.centaurfloors.com